

**INFINO VB-3100G**

(PBT+ABS)-GF10

Lotte Chemical Corporation

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	30	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Melt Flow Index, MFI	30	g/10min	ASTM D 1238
Temperature	250	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.009	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	70	MPa	ISO 527
Strain at break	4	%	ISO 527
Flexural modulus, 23°C	3500	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Charpy notched impact strength, +23°C	2.8	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	4	kJ/m <sup>2</sup>	ISO 180/1A
Rockwell hardness	R 113	-	ISO 2039-2
<b>ASTM Data</b>			
Tensile Strength at Yield	74	MPa	ASTM D 638
Elongation at Break	4	%	ASTM D 638
Flexural Modulus	3900	MPa	ASTM D 790
Flexural Strength	98	MPa	ASTM D 790
Rockwell Hardness	R 113	-	ASTM D 785
Izod Impact notched, 1/8 in	49	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	125	°C	ISO 75-1/-2
Vicat softening temperature, B	147	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	135	°C	ASTM D 648
<b>Other properties</b>			
Water absorption	0.08	%	Sim. to ISO 62
Density	1450	kg/m <sup>3</sup>	ISO 1183
Density	1450	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.05	%	-
Melt temperature	250	°C	-
Mold temperature	60 - 120	°C	-
Zone 1	210 - 220	°C	-
Zone 2	225 - 230	°C	-
Zone 3	240 - 250	°C	-
Nozzle temperature	250	°C	-
Screw speed	50 - 150	rpm	-

**INFINO VB-3100G**

(PBT+ABS)-GF10

Lotte Chemical Corporation

Injection pressure	<b>49 - 250</b>	MPa	-
Back pressure	<b>0.5 - 2</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Applications**

Electrical and Electronical

**Delivery form**

Pellets, Natural Color

**Regional Availability**

North America, Europe, Asia Pacific