

Product Texts

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® XT70G35HSL BK044A is a 35% glass fiber reinforced, heat stabilized polyamide 66 resin for injection molding. It has been developed for automotive applications requiring good retention of properties over time at temperatures up to 220°C and with good high temperature fatigue and properties.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577
^[C] Density of melt	1240	kg/m ³	-
^[C] Thermal conductivity of melt	0.25	W/(m K)	-
^[C] Spec. heat capacity of melt	2050	J/(kg K)	-
^[C] Ejection temperature	200	°C	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11000 / 7500	MPa	ISO 527
^[C] Stress at break	200 / 140	MPa	ISO 527
^[C] Strain at break	3.2 / 5	%	ISO 527
^[C] Charpy impact strength, +23°C	90 / 100	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	80 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	13 / 16	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	258 / *	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	65 / *	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	240 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	19 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	90 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion -40°C to +100°C, parallel	19	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion -40°C to +100°C, normal	90	E-6/K	ISO 11359-1/-2
^[C] Burning rate, FMVSS, Thickness 1 mm	33	mm/min	ISO 3795 (FMVSS 302)

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Humidity absorption	2.1 / *	%	Sim. to ISO 62
^[C] Density	1410 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	140 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Additives

Lubricants, Release agent

Special Characteristics

Heat stabilized or stable to heat

Features

Fatigue Resistance

Chemical Resistance

General Chemical Resistance

Applications

Automotive, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America

Other text information**Injection molding**