

4LAC 13H20000

ABS

4Plas

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2450	MPa	ISO 527
Yield stress	35	MPa	ISO 527
Yield strain	2	%	ISO 527
Strain at break	8	%	ISO 527
Izod notched impact strength, +23°C	12	kJ/m ²	ISO 180/1A
Other properties			
Density	1100	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Europe