

**Staramide AG8**

PA66-GF40

Eurostar Engineering Plastics

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Thermal conductivity of melt	0.33	W/(m K)	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	12000	MPa	ISO 527
Stress at break	205	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	11000	MPa	ISO 178
Izod notched impact strength, +23°C	13	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	11	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-40	°C	-
Rockwell hardness	L 114	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	258	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	260	°C	ISO 75-1/-2
Vicat softening temperature, B	260	°C	ISO 306
Coeff. of linear therm. expansion, parallel	21	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	73	E-6/K	ISO 11359-1/-2
Oxygen index	27	%	ISO 4589-1/-2
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
Dissipation factor, 1MHz	150	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	19	kV/mm	IEC 60243-1
Comparative tracking index	500	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	3	%	Sim. to ISO 62
Humidity absorption	0.9	%	Sim. to ISO 62
Density	1460	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Features**

Low Odor

**Delivery form**

Pellets

**Regional Availability**

Europe