

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Strength	245	MPa	ISO 527
Flexural modulus, 23°C	12000	MPa	ISO 178
Charpy notched impact strength, +23°C	16	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Strength	216	MPa	ASTM D 638
Flexural Modulus	11770	MPa	ASTM D 790
Flexural Strength	333	MPa	ASTM D 790
Rockwell Hardness	R 125	-	ASTM D 785
Izod Impact notched, 1/8 in	108	J/m	ASTM D 256
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	255	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	255	°C	ISO 75-1/-2
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.8	mm	-
Coefficient of Thermal Expansion, MD	20	E-6/K	ASTM D 696
DTUL @ 66 psi	250	°C	ASTM D 648
DTUL @ 264 psi	247	°C	ASTM D 648
Melting Temperature	255	°C	ASTM D 3418
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	21	kV/mm	ASTM D 149
Dielectric Constant, 1 MHz	3.6	-	ASTM D 150
Arc Resistance	135	s	ASTM D 495
Other properties			
Density	1520	kg/m ³	ISO 1183
Water Absorption, 24hr	0.3	%	ASTM D 570
Density	1500	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	4 - 5	h	-
Processing humidity	≤0.05	%	-
Mold temperature	60 - 80	°C	-
Zone 1	270	°C	-
Zone 2	290	°C	-
Zone 3	295	°C	-
Nozzle temperature	300	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Asia Pacific