

N6345G-BK1D

PA66-GF45

Pontex Polyblend Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	167	MPa	ASTM D 638
Flexural Modulus	12750	MPa	ASTM D 790
Flexural Strength	245	MPa	ASTM D 790
Izod Impact notched, 1/8 in	108	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1500	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

Asia Pacific