

Product Texts

Base Polymer	Polyamide 66
Filler/Additive System	50 % glass fibres
Special Features	various
Typical Applications	various

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	15500 / 12000	MPa	ISO 527
^[C] Stress at break	215 / 165	MPa	ISO 527
^[C] Strain at break	2.6 / 3.5	%	ISO 527
^[C] Charpy impact strength, +23°C	80 / 85	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	12 / 18	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	260 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1560 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions 80 °C in a dry air (dessiccant) dryer for 2-12 h

Processing Injection Moulding melt temperature 280-300 °C
mould temperature 80-120 °CStorage dry, protected from light
not above 30°C