

**4MID 9A20500 FR7**

PA66

4Plas

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	3500	MPa	ISO 527
Stress at break	80	MPa	ISO 527
Strain at break	5	%	ISO 527
Izod notched impact strength, +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	4	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	210	°C	ISO 75-1/-2
Vicat softening temperature, B	245	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Comparative tracking index	600	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1160	kg/m <sup>3</sup>	ISO 1183
Moisture Content	0.2	%	-

**Characteristics****Special Characteristics**

Flame retardant, Halogen-free, Heat stabilized or stable to heat

**Regional Availability**

Europe