

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	1.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.5 / *	%	ISO 294-4, 2577
Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3000 / 1400	MPa	ISO 527
Yield stress	67 / 47	MPa	ISO 527
Flexural modulus, 23°C	2850 / 1600	MPa	ISO 178
Charpy impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	15 / 25	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	9 / -	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	93 / -	MPa	ISO 2039-1
Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	263 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	67 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	213 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
Comparative tracking index	600 / -	-	IEC 60112
Other properties	dry / cond	Unit	Test Standard
Density	1100 / -	kg/m <sup>3</sup>	ISO 1183
Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	320	°C	-
Mold temperature	100	°C	-
Injection pressure	75	MPa	-

## Characteristics

### Processing

Injection Molding

### Delivery form

Black

### Special Characteristics

High impact or impact modified

### Applications

Automotive, Electrical and Electronical

### Regional Availability

Europe, Asia Pacific