

**PRECITE® V GF 30 2 black (7724)**

(PBT+ASA)-GF30

Akro-Plastic GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	9400	MPa	ISO 527
Stress at break	130	MPa	ISO 527
Strain at break	2.4	%	ISO 527
Charpy impact strength, +23°C	60	kJ/m <sup>2</sup>	ISO 179/1eU
Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Other properties	Value	Unit	Test Standard
Density	1430	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Black

**Applications**

Automotive, Electrical and Electronical

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

Europe, Asia Pacific

**Features**

Low Warpage