

**Product Texts**

Base Polymer	Polyamide 66
Special Features	heat stabilised,easy release (demoulding),easy flow,adhesion-modified to PVC
Typical Applications	various

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	6	cm <sup>3</sup> /10min	ISO 1133
Temperature	275	°C	-
Load	5	kg	-

[C]: CAMPUS

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2500	MPa	ISO 527
<sup>[C]</sup> Yield stress	65	MPa	ISO 527
<sup>[C]</sup> Yield strain	5	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	15	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	70	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	220	°C	ISO 306

[C]: CAMPUS

**Other properties**

	Value	Unit	Test Standard
<sup>[C]</sup> Density	1130	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Special Characteristics**

High impact or impact modified

**Other text information****Injection molding**

Pre-Drying Conditions 80 °C in a dry air (dessiccant) dryer  
for 2-12 h  
dependant on moisture content  
max. moisture content <0,15 %

Processing Injection Moulding melt temperature 270-290 °C  
mould temperature 40-80 °C

Storage dry, protected from light  
not above 30°C