

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2200 / 1400	MPa	ISO 527
Yield stress	52 / 45	MPa	ISO 527
Yield strain	5.4 / 18	%	ISO 527
Nominal strain at break	30 / -	%	ISO 527
Charpy impact strength, +23°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	25 / -	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	140 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 1MHz	3.2 / -	-	IEC 62631-2-1
Dissipation factor, 1MHz	165 / -	E-4	IEC 62631-2-1
Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
Comparative tracking index	500 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	6.8 / *	%	Sim. to ISO 62
Humidity absorption	2.2 / *	%	Sim. to ISO 62
Density	1090 / -	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Melt temperature	280 - 300	°C	-
Mold temperature	60 - 80	°C	-

## Characteristics

### Processing

Injection Molding

### Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa