

Bergamid™ A70 ZKW

PA66

Avient Corporation

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3000	MPa	ISO 527
Yield stress	84	MPa	ISO 527
Yield strain	8.5	%	ISO 527
Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Delivery form

Pellets