

**Product Texts**

Flammability @0.8mm nom. V-2  
thickn. -

**Processing/Physical Characteristics**

**ISO Data**

	dry / cond	Unit	Test Standard
<sup>[C]</sup> Molding shrinkage, parallel	1.2 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.2 / *	%	ISO 294-4, 2577

[C]: CAMPUS

**Mechanical properties**

**ISO Data**

	dry / cond	Unit	Test Standard
<sup>[C]</sup> Tensile Modulus	3350 / 1575	MPa	ISO 527
<sup>[C]</sup> Yield stress	85 / 58	MPa	ISO 527
<sup>[C]</sup> Yield strain	4.3 / 20	%	ISO 527
<sup>[C]</sup> Charpy notched impact strength, +23°C	4 / 12.5	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

**ISO Data**

	dry / cond	Unit	Test Standard
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	66 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	204 / *	°C	ISO 75-1/-2

[C]: CAMPUS

**Other properties**

	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	- / 1140	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Delivery form**

Natural Color