

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	11000	MPa	ISO 527
Stress at break	175	MPa	ISO 527
Strain at break	2.8	%	ISO 527
Charpy impact strength, +23°C	60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	245	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	260	°C	ISO 75-1/-2
Vicat softening temperature, B	255	°C	ISO 306
Electrical properties			
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257
Other properties			
Density	1330	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	270 - 290	°C	-
Mold temperature	80 - 100	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Special Characteristics

Increased electrical conductivity