

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>9900 / 9400</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>157 / 132</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>3.3 / 3.3</b>	%	ISO 527
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>11 / 11</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Burning Behav. at thickness h	<b>V-0 / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-
Yellow Card available	<b>yes / *</b>	-	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Comparative tracking index	<b>500 / -</b>	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Humidity absorption	<b>1.6 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1380 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa