

LUVOTECH GS 58

PA66-GF

LEHVOSS Group

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	13500	MPa	ISO 527
Tensile Strength	250	MPa	ISO 527
Flexural modulus, 23°C	12000	MPa	ISO 178
Charpy impact strength, +23°C	95	kJ/m ²	ISO 179/1eU
Thermal properties			
ISO Data			
Vicat softening temperature, A	250	°C	ISO 306
Electrical properties			
ISO Data			
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Other properties			
Density	1480	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	75	°C	-
Pre-drying - Time	6 - 16	h	-
Processing humidity	≤0.1	%	-
Melt temperature	290	°C	-
Mold temperature	90 - 120	°C	-
Zone 1	290 - 310	°C	-
Zone 2	290 - 310	°C	-
Zone 3	290 - 310	°C	-
Nozzle temperature	280 - 300	°C	-

Characteristics**Processing**

Injection Molding

Features

Tribologic Grade

Applications

Automotive, IT / Business Machine

Regional Availability

North America, Europe, Asia Pacific