

Staramide AG2LT2

PA66-GF

Eurostar Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	90	MPa	ISO 527
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	240	°C	ISO 75-1/-2
Electrical properties			
ISO Data			
Comparative tracking index	350	-	IEC 60112
Other properties			
Density	1270	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Additives

Lubricants