

**Staramide AG3X3**

PA66-GF

Eurostar Engineering Plastics

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>4800</b>	MPa	ISO 527
Stress at break	<b>100</b>	MPa	ISO 527
Strain at break	<b>3.7</b>	%	ISO 527
Flexural modulus, 23°C	<b>4100</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>70</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	<b>50</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>13</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	<b>8</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	<b>65</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	<b>10</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>6</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>-40</b>	°C	-
Rockwell hardness	<b>L 121</b>	-	ISO 2039-2
Ball indentation hardness	<b>131</b>	MPa	ISO 2039-1

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>242</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>35</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	<b>100</b>	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>0.75</b>	mm	-

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Electric strength	<b>16</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>600</b>	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water absorption	<b>6.5</b>	%	Sim. to ISO 62
Humidity absorption	<b>1.3</b>	%	Sim. to ISO 62
Density	<b>1160</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Features**

Low Odor

**Delivery form**

Pellets

**Regional Availability**

Europe

**Special Characteristics**

High impact or impact modified