

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	13000	MPa	ISO 527
^[C] Stress at break	205	MPa	ISO 527
^[C] Strain at break	2	%	ISO 527
^[C] Charpy notched impact strength, +23°C	23	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1460	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Features

Long fiber reinforced

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific