

CELSTRAN® PA66-GF50-28 AD3020

PA66-GLF50

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	16100	MPa	ISO 527
^[C] Stress at break	235	MPa	ISO 527
^[C] Strain at break	1.8	%	ISO 527
^[C] Charpy notched impact strength, +23°C	37	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1560	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Additives**

Lubricants

Features

Long fiber reinforced

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific