

Product Texts

Injection Molding, Unreinforced, Flame Retardant, Improved Impact, Low Warpage

ISO 1043 (PBT+PC)-I FR(17)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
^[C] Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.8	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2400	MPa	ISO 527
^[C] Yield stress	45	MPa	ISO 527
^[C] Yield strain	2.9	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	170	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	10	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	80	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	100	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
^[C] Burning Behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	1.5	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.3	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	2.9	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	250	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	140	E-4	IEC 62631-2-1
^[C] Electric strength	30	kV/mm	IEC 60243-1
^[C] Comparative tracking index	300	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1310	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	250	°C	ISO 294
Injection Molding, mold temperature	60	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.02	%	-
Melt temperature	240 - 260	°C	-
Mold temperature	60 - 80	°C	-

Characteristics**Processing**

Injection Molding

Features

Low Warpage

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Special Characteristics

Flame retardant, High impact or impact modified, Heat stabilized or stable to heat

Other text information**Injection molding**

PREPROCESSING

Residual moisture content: 0.00 - 0.02 %

Drying temperature circulating air dryer: 100 °C

Drying time circulating air dryer: 4 - 8 h

PROCESSING

Melt temperature (Tmin - Tmax): 240 - 260 °C

admissible residence time at Tmax: <5 min

Mold temperature: 60 - 80 °C