Durethan® AKV320ZH2.0 900116

PA66-I-GF20 Envalior

Product Texts

Blow Molding Grade, 20% Glass Reinforced, Heat Stabilized, Improved Impact, Excellent Surface Properties

ISO 1043 PA66-I-GF20

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**6400 / 3500**	MPa	ISO 527
[C] Stress at break	**120 / 75**	MPa	ISO 527
[C] Strain at break	**4.9 / 17.6**	%	ISO 527
[C] Charpy impact strength, +23°C	**85 / 115**	kJ/m²	ISO 179/1eU
[C] Charpy impact strength, -30°C	**95 / 115**	kJ/m²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	**15 / 30**	kJ/m²	ISO 179/1eA
[C] Charpy notched impact strength, -30°C	**- / 10**	kJ/m²	ISO 179/1eA
[C] Puncture - maximum force, +23°C	**1000 / 2100**	N	ISO 6603-2
[C] Puncture - maximum force, -30°C	**700 / 850**	N	ISO 6603-2
[C] Puncture energy, +23°C	**4.6 / 11.2**	J	ISO 6603-2
[C] Puncture energy, -30°C	**3.2 / 3.7**	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Melting temperature, 10°C/min	**259 / ***	°C	ISO 11357-1/-3
[C] Temp. of deflection under load, 1.80 MPa	**221 / ***	°C	ISO 75-1/-2
[C] Temp. of deflection under load, 0.45 MPa	**250 / ***	°C	ISO 75-1/-2
[C] Coeff. of linear therm. expansion, parallel	**30 / ***	E-6/K	ISO 11359-1/-2
[C] Coeff. of linear therm. expansion, normal	**120 / ***	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Water absorption	**7 / ***	%	Sim. to ISO 62
[C] Humidity absorption	**2 / ***	%	Sim. to ISO 62
[C] Density	**1250 / -**	kg/m³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
[C] Injection Molding, melt temperature	**290**	°C	ISO 294
Injection Molding, mold temperature	**80**	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**80**	°C	-
Pre-drying - Time	**2 - 6**	h	-
Processing humidity	**≤0.06**	%	-
Melt temperature	**280 - 300**	°C	-
Mold temperature	**80 - 120**	°C	-

Characteristics

Processing

Blow Molding, Thermoforming

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

Other text information

Injection molding

PREPROCESSING
Residual moisture content: 0.00 - 0.06%
Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING
Melt temperature (Tmin - Tmax): 280 - 300 °C

Mold temperature: 80 - 120 °C

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.