

**Product Texts**

Extrusion, Medium/High Viscosity, Highly lubricated, Food Contact Quality

ISO 1043 PA6/66

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>10 / *</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>230 / *</b>	°C	-
Load	<b>2.16 / *</b>	kg	-

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>200 / *</b>	°C	ISO 11357-1/-3

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Humidity absorption	<b>2.8 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1130 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

<b>Material specific properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Viscosity number	<b>183 / *</b>	cm <sup>3</sup> /g	ISO 307, 1157, 1628

[C]: CAMPUS

**Characteristics**

**Processing**  
Film Extrusion, Other Extrusion

**Additives**  
Lubricants

**Delivery form**  
Pellets

**Regional Availability**  
Asia Pacific