

Tisblend® FL 15D03 K02 R01

(PBT+PET)-GF15

Tisan Engineering Plastics Co.Ltd.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	5000	MPa	ISO 527
Stress at break	92.5	MPa	ISO 527
Izod notched impact strength, +23°C	10.5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	240	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1420	kg/m ³	ISO 1183
Moisture Content	0.2	%	-

Characteristics**Delivery form**

Pellets, Natural Color

Regional Availability

Europe, Near East/Africa