

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	4700	MPa	ISO 527
Stress at break	110	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A
Rockwell hardness	R 120	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	215	°C	ISO 75-1/-2
Vicat softening temperature, B	220	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1260	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	260 - 290	°C	-
Mold temperature	90	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific