

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9800 / 6500	MPa	ISO 527
^[C] Stress at break	185 / 115	MPa	ISO 527
^[C] Strain at break	3 / 7	%	ISO 527
Flexural modulus, 23°C	8300 / 4700	MPa	ISO 178
Flexural strength	235 / 140	MPa	ISO 178
^[C] Charpy impact strength, +23°C	80 / 92	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	11 / 16	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	242 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	230 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / >1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	30 / -	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1370 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Applications

Automotive

Features

Copolymer