

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.0 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9800 / 5000	MPa	ISO 527
^[C] Stress at break	175 / 100	MPa	ISO 527
^[C] Strain at break	3.3 / 9	%	ISO 527
Flexural modulus, 23°C	8800 / 5000	MPa	ISO 178
Flexural strength	260 / 160	MPa	ISO 178
^[C] Charpy impact strength, +23°C	70 / 90	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10 / 16	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	242 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	230 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / >1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	34 / -	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1370 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Features

Copolymer

Delivery form

Black

Applications

Automotive

Special Characteristics

Heat stabilized or stable to heat