

**MAPEX® AN2620PB**

PA666-GF33

Ginar Technology Co.,Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.003</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>134</b>	MPa	ASTM D 638
Elongation at Break	<b>2.5</b>	%	ASTM D 638
Flexural Modulus	<b>8960</b>	MPa	ASTM D 790
Flexural Strength	<b>207</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>80</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>3.2</b>	mm	-
DTUL @ 264 psi	<b>225</b>	°C	ASTM D 648
Melting Temperature	<b>260</b>	°C	ASTM D 3418

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water Absorption, 24hr	<b>0.3</b>	%	ASTM D 570
Density	<b>1380</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Certifications**

RoHS compliant

**Regional Availability**

Europe, Asia Pacific