

**Product Texts**

Vydyne R633H01 is 33% glass-fiber reinforced PA66/6 copolymer resin for superior surface appearance. Available in black, this injection-molding grade resin is lubricated for machine feed and mold release.

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	10800 / 8000	MPa	ISO 527
<sup>[C]</sup> Stress at break	184 / 130	MPa	ISO 527
<sup>[C]</sup> Strain at break	4 / 6	%	ISO 527
Flexural modulus, 23°C	8800 / 6800	MPa	ISO 178
Flexural strength	255 / 195	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	51 / 92	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	44 / 91	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	12 / 25	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	11 / 15	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	13 / 22	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	12 / 19	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	233 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	220 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	230 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	15 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	100 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Comparative tracking index	325 / -	-	IEC 60112
<b>ASTM Data</b>			
Arc Resistance	150 / -	s	ASTM D 495

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	1.3 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	2.3 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1390 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-

Melt temperature	<b>285 - 305</b>	°C	-
Mold temperature	<b>65 - 95</b>	°C	-
Zone 1	<b>280 - 310</b>	°C	-
Zone 2	<b>280 - 310</b>	°C	-
Zone 3	<b>280 - 310</b>	°C	-
Nozzle temperature	<b>280 - 310</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets, Black

**Additives**

Lubricants, Release agent

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Copolymer

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific