

CELSTRAN® PA66-GF40-01

PA666-GLF40

Celanese

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Charpy impact strength, +23°C	91 / 91	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	65 / 65	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	36 / 36	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	36 / 37	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	- / 1460	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Long fiber reinforced

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific