

Product Texts

Product-nomenclature: ISO 16396-PA 66 PA6,MD30,M1HR,C14-050N

Product Attributes

Improved heat resistance

Markets

Automotive

Fuel systems, Powertrain and Chassis, Exterior

Electricals & Electronics

Electrical appliances, Electrical equipment

Industry & Consumer goods

Housewares, Mechanical Engineering, Sports & Leisure, Tools & Accessories

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.7 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.1 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6000 / 2600	MPa	ISO 527
^[C] Stress at break	85 / 50	MPa	ISO 527
^[C] Strain at break	7 / 25	%	ISO 527
^[C] Charpy impact strength, +23°C	70 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	70 / 70	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	5 / 7	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	4 / 4.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	90 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 8.00 MPa	60 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	80 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	80 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E11 / 1E10	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E11	Ohm	IEC 62631-3-2
^[C] Electric strength	25 / 21	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 500	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	6.5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2 / *	%	Sim. to ISO 62
^[C] Density	1370 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Granules, Natural Color

Special Characteristics

Heat stabilized or stable to heat

Applications

Automotive, Electrical and Electronical, Sports Equipment

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa