

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength at Yield | 83 | MPa | ASTM D 638 |
| Elongation at Break | 9 | % | ASTM D 638 |
| Flexural Modulus | 5169 | MPa | ASTM D 790 |
| Flexural Strength | 145 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 75 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| DTUL @ 264 psi | 145 | °C | ASTM D 648 |
| Melting Temperature | 260 | °C | ASTM D 3418 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1370 | kg/m ³ | ASTM D 792 |

Characteristics

Delivery form

Natural Color

Certifications

RoHS compliant

Features

Low Warpage

Regional Availability

Europe, Asia Pacific