

Product Texts

Injection Molding, 30% Glass Reinforced, Excellent Surface Properties

ISO 1043 (PBT+PET)-GF30

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	30	cm ³ /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
^[C] Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	10400	MPa	ISO 527
^[C] Stress at break	145	MPa	ISO 527
^[C] Strain at break	2.8	%	ISO 527
^[C] Tensile creep modulus, 1h	10000	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	8500	MPa	ISO 899-1
^[C] Charpy impact strength, +23°C	65	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	55	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	10	kJ/m ²	ISO 179/1eA
^[C] Puncture - maximum force, +23°C	650	N	ISO 6603-2
^[C] Puncture energy, +23°C	2.1	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	90	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
^[C] Burning rate, FMVSS, Thickness 1 mm	47.8	mm/min	ISO 3795 (FMVSS 302)
^[C] Oxygen index	21	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	4	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.8	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	18	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	170	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	27	kV/mm	IEC 60243-1
^[C] Comparative tracking index	250	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.3	%	Sim. to ISO 62
^[C] Humidity absorption	0.1	%	Sim. to ISO 62
^[C] Density	1550	kg/m ³	ISO 1183

[C]: CAMPUS

Pocan® T7331 000000

(PBT+PET)-GF30

Envalior

Material specific properties	Value	Unit	Test Standard
ISO Data			
^[C] Viscosity number	91	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	270	°C	ISO 294
Injection Molding, mold temperature	90	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.02	%	-
Melt temperature	260 - 280	°C	-
Mold temperature	80 - 100	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Additives

Release agent

Other text information**Injection molding****PREPROCESSING**

Residual moisture content: 0.00 - 0.02 %

Drying temperature circulating air dryer: 120 °C

Drying time circulating air dryer: 4 - 8 h

PROCESSING

Melt temperature (Tmin - Tmax): 260 - 280 °C

Mold temperature: 80 - 100 °C