

**Product Texts**

Easy flow 30% glass fibre reinforced flame retardant PBT/PET compound with halogenated agent; without PBDE

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	54	cm <sup>3</sup> /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	12000	MPa	ISO 527
<sup>[C]</sup> Stress at break	148	MPa	ISO 527
<sup>[C]</sup> Strain at break	2	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	46	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	40	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	7	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	7	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	198	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	219	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	190	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Burning Behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Oxygen index	34	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	>1E15	Ohm	IEC 62631-3-2
<sup>[C]</sup> Comparative tracking index	225	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1680	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	240 - 255	°C	-
Mold temperature	80 - 100	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Granules

**Additives**

Release agent

**Special Characteristics**

Flame retardant

**Regional Availability**North America, Europe, Asia Pacific, South and Central America,  
Near East/Africa**Other text information****Injection molding**PREPROCESSING; **Pretreatment**

Predrying: 4-6 h / 80°C

**PROCESSING ;Processing:**

Melttemperature	240 - 255	°C
Mouldtemperature	80 - 100	°C