

**Matrixx 662E0**

PA66

LyondellBasell Industries

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>79.3</b>	MPa	ASTM D 638
Flexural Modulus	<b>2930</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>59</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>196</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>70</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1140</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>71 - 82</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Melt temperature	<b>271 - 293</b>	°C	-
Mold temperature	<b>52 - 82</b>	°C	-
Zone 1	<b>249 - 293</b>	°C	-
Zone 2	<b>249 - 293</b>	°C	-
Zone 3	<b>249 - 293</b>	°C	-
Back pressure	<b>&lt;0.689</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America

**Delivery form**

Pellets