

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	17000	MPa	ISO 527
Stress at break	145	MPa	ISO 527
Strain at break	2	%	ISO 527
Izod notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	10	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	240	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	210	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1730	kg/m <sup>3</sup>	ISO 1183
Moisture Content	0.08	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	260 - 280	°C	-
Mold temperature	60 - 110	°C	-
Feed temperature	50 - 70	°C	-
Holding pressure	40 - 80	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Black

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Regional Availability**

Europe