

**Product Texts**

Vydyne 21A1 is general-purpose PA66 resin. It is offered in natural and designed for extrusion-compounding applications. 21A1 provides the chemical resistance typical of PA66 to many chemicals, machine and motor oils, solvents and gasoline. 21A1 exhibits good initial color and color retention after compounding.

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>260 / *</b>	°C	ISO 11357-1/-3

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1140 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Other Extrusion

**Chemical Resistance**

General Chemical Resistance, Solvent Resistance, Oil Resistance

**Delivery form**

Pellets, Natural Color

**Applications**

General Purpose

**Features**

Color Stability

**Regional Availability**

North America, Europe, Asia Pacific