

Product Texts

Low Viscosity, Neat resin, Food Contact Quality

ISO 1043 PA6

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Density of melt	960	kg/m ³	-
^[C] Thermal conductivity of melt	0.23	W/(m K)	-
^[C] Spec. heat capacity of melt	2680	J/(kg K)	-
^[C] Eff. thermal diffusivity	8.82E-8	m ² /s	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2700 / -	MPa	ISO 527
^[C] Yield stress	80 / -	MPa	ISO 527
^[C] Yield strain	4.2 / -	%	ISO 527
^[C] Charpy impact strength, +23°C	N / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	5 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	9.5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2.5 / *	%	Sim. to ISO 62
^[C] Density	1130 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	132 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics**Processing**

Other Extrusion

Certifications

Food contact

Delivery form

Pellets

Regional Availability

North America