

Bergamid™ B800 H grey VN4155CF UV

PA6

Avient Corporation

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2800	MPa	ISO 527
Yield stress	85	MPa	ISO 527
Yield strain	3.5	%	ISO 527
Flexural modulus, 23°C	2700	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	54	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	2.7	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	170	°C	ISO 75-1/-2
Electrical properties			
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Other properties			
Density	1130	kg/m ³	ISO 1183

Characteristics**Delivery form**

Pellets

Regional Availability

Europe, Asia Pacific, Near East/Africa

Special Characteristics

U.V. stabilized or stable to weather