

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	20200	MPa	ISO 527
^[C] Stress at break	230	MPa	ISO 527
^[C] Strain at break	1.65	%	ISO 527
^[C] Charpy notched impact strength, +23°C	36	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets, Black