

DOMAMID 6IK1 302 NC

PA6

DOMO Engineering Plastics

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.7	%	ISO 294-4, 2577
Molding shrinkage, normal	1.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2700	MPa	ISO 527
Yield stress	65	MPa	ISO 527
Stress at break	50	MPa	ISO 527
Strain at break	20	%	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	221	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	240 - 280	°C	-
Mold temperature	60 - 80	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Natural Color

Regional Availability

North America, Europe, Asia Pacific