

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>2650</b>	MPa	ISO 527
Yield stress	<b>66</b>	MPa	ISO 527
Stress at break	<b>35</b>	MPa	ISO 527
Strain at break	<b>30</b>	%	ISO 527
Flexural modulus, 23°C	<b>2300</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>11</b>	kJ/m <sup>2</sup>	ISO 179/1eA

### Characteristics

#### Delivery form

Natural Color

#### Regional Availability

North America, Europe, Asia Pacific