

DOMAMID S 6FC

PA6

DOMO Engineering Plastics

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3100	MPa	ISO 527
Yield stress	80	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus, 23°C	2700	MPa	ISO 178
Charpy notched impact strength, +23°C	4.5	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	4.5	kJ/m ²	ISO 180/1A
Rockwell hardness	R 120	-	ISO 2039-2
Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	221	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	175	°C	ISO 75-1/-2
Vicat softening temperature, B	200	°C	ISO 306
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	600	-	IEC 60112
Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ISO 1183
Material specific properties	Value	Unit	Test Standard
ISO Data			
Viscosity number	145	cm ³ /g	ISO 307, 1157, 1628
Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	230 - 250	°C	-
Mold temperature	60 - 90	°C	-

Characteristics**Processing**

Injection Molding

Certifications

Food contact

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific