

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3300 / 1400	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	5 / 10	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	9.3 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2.6 / *	%	Sim. to ISO 62
^[C] Density	- / 1130	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Black

Certifications

Recycled Resin Content