

EPLAMID 6 IMP NC Q1D001

PA6

Epsan Plastik San. Tic. A.Ş

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.8 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	2.2 / *	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	1200 / 650	MPa	ISO 527
Stress at break	25 / 15	MPa	ISO 527
Strain at break	>50 / >50	%	ISO 527
Flexural modulus, 23°C	1150 / -	MPa	ISO 178
Charpy notched impact strength, +23°C	85 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	80 / -	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	45 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	120 / *	°C	ISO 75-1/-2
Vicat softening temperature, B	160 / *	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Other properties			
Density	1040 / -	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	260	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Additives

Lubricants

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Applications

Automotive, General Purpose, Sports Equipment

Regional Availability

Europe