

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3000	MPa	ISO 527
Yield stress	80	MPa	ISO 527
Strain at break	20	%	ISO 527
Flexural modulus, 23°C	2700	MPa	ISO 178
Flexural strength	100	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	4	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	70	°C	ISO 75-1/-2
Vicat softening temperature, B	200	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	220 - 240	°C	-
Mold temperature	60 - 80	°C	-

Characteristics

Processing

Injection Molding

Certifications

RoHS compliant

Applications

Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America