

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.014	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	81	MPa	ASTM D 638
Flexural Modulus	2746	MPa	ASTM D 790
Flexural Strength	123	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	74	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	80	E-6/K	ASTM D 696
DTUL @ 66 psi	180	°C	ASTM D 648
DTUL @ 264 psi	65	°C	ASTM D 648
Melting Temperature	220	°C	ASTM D 3418
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	20	kV/mm	ASTM D 149
Dielectric Constant, 1 MHz	3.4	-	ASTM D 150
Arc Resistance	120	s	ASTM D 495
Other properties			
Density	1140	kg/m ³	ASTM D 792

Characteristics

Delivery form

Black

Regional Availability

North America, Asia Pacific

Additives

Release agent