

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	128	MPa	ASTM D 638
Flexural Modulus	7355	MPa	ASTM D 790
Flexural Strength	216	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	59	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	40	E-6/K	ASTM D 696
DTUL @ 66 psi	210	°C	ASTM D 648
DTUL @ 264 psi	203	°C	ASTM D 648
Melting Temperature	220	°C	ASTM D 3418
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Dielectric Strength, Short Time	22	kV/mm	ASTM D 149
Dielectric Constant, 1 MHz	3.5	-	ASTM D 150
Arc Resistance	136	s	ASTM D 495
<b>Other properties</b>			
Water Absorption, 24hr	0.4	%	ASTM D 570
Density	1460	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Delivery form

Black

#### Regional Availability

North America, Asia Pacific

#### Special Characteristics

Heat stabilized or stable to heat