

# Novamid® 1007J

PA6

Envalior

## Product Texts

Injection Molding, Low Viscosity

ISO 1043 PA6

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	84 / *	cm <sup>3</sup> /10min	ISO 1133
Temperature	230 / *	°C	-
Load	2.16 / *	kg	-

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Humidity absorption	2.8 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1130 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Viscosity number	99 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

[C]: CAMPUS

## Characteristics

### Processing

Other Extrusion

### Regional Availability

Asia Pacific

### Delivery form

Pellets

## Other text information

### Injection molding

[Injection Molding Recommendations](#)